

Teflex Woven

- Teflex Woven is a pure woven PTFE.
- Teflex Woven is capable of running at high temperatures.
- Continuously operating at 260°C / 500°F with short term surges at 280°C / 536°F.
- Can be used on products across the full pH scale, i.e. either caustic or acid products will not effect Teflex Woven.

*** VIBRATION

















PHYSICAL PROPERTIES:

| Fibre | PTFE |
|---|------------------------------------|
| Colour | Natural (dark brown) |
| Construction/finish | Basket weave |
| Weight | 678 g/m ² |
| | 20 oz/yd ² |
| Thickness (mm) | 0.5mm / 1/64" |
| Max. Operating Temp | 260°C / 500°F |
| Max. Surge Temp | 280°C / 536°F |
| Low Temp Flexibility | Good |
| Surface Resistance (Ohms) | Insulative |
| Minimum Tensile Strength measured as a force over a 25mm wide Ravel Strip (Test Standard: ASTM D5035) | Fabric Warp 90) kgf/25mm Weft 100) |
| Ultimate Elongation (%) (Test Standard: ASTM D5035) | 55 |
| | |

Air Permeability:

(cm³/cm² sec@125Pa) 0.3 (ft³/ft²/min@0.5" wg) 0.5

AVAILABLE SIZES: (in 50mm / 2" increments)

| Diameter | Ø100mm, 150mm to |
|--------------------|--|
| (also available in | 1,650mm |
| 125mm/5") | (4", 5" to 65") |
| Length | 80mm , 100mm to 1,500mm (3", 4" to 59 1/16") |

NB: Some size restrictions apply for TR versions, larger diameters and connectors with rings.

COMPLIANCE:

Atex Compliant: IBExU tested. Can be used in certain dust explosion hazardous areas (restrictions apply). PTFE is compliant with FDA 21 CFR 177.1550, 178.3297.